

GRAPHITE TREATED E-GLASS CLOTH

<u>Finished Fabric</u>	<u>Units</u>	<u>Value</u>	<u>Tolerance</u>
Weight	g/m ²	1100	±5%
Thickness	mm	1.3	±5%
Useable width (standard)	mm	1000	±5%
Roll Length (standard)	mtr	25	
Maximum operating temp.	°C	600*	
Colour/Description	Black fibres both sides		

Base Fabric Construction

Weight	g/m ²	1000	±5%
Weave pattern		Plain	
Construction			
Warp	per cm	5.0	±5%
Weft	per cm	3.0	±5%
Yarn count			
Warp	Tex	ET9 1250	
Weft	Tex	ET9 1250	
Tensile strength			
Warp	N/5cm	4500	±10%
Weft	N/5cm	2600	±10%

Treatment/Coating Details

Weight	g/m ²	100	±10%
--------	------------------	-----	------

100g/m² Graphite/silicone solution evenly distributed across both sides

Comments

*Base fabric will withstand 600°C (unstressed), melting point >800°C

The graphite solution increases the fabric temperature resistance, and can improve its performance where flexing is involved.

Glass fibre is inherently non-flammable, and the finished product is non-combustible.

If you have any technical queries please feel free to phone us: 01422 311 607.

THS Industrial Textiles Ltd reserves the right to alter any of the elements quoted in the above specification without prior notice. Please note that the above information is given in good faith and should be considered as a guide only, if any values in this specification are of critical importance then we strongly recommend the user arranges independent testing themselves. Test methods mentioned are considered as guides only, actual methods may differ slightly in practice. Suitability of the product for all applications is at the discretion of the user, as are any potential patent infringements relating to specific applications.